

Seamless OCTG (casing) - Performance Properties													
O.D. (in.)	Nominal Weight T&C (lbs/ft)	Plain - End Weight (lbs/ft)	Grade	Collapse Resistance (psi)	Internal Yield Pressure at Min. Yield (psi) PE	Internal Yield Pressure at Min. Yield (psi) STC	Internal Yield Pressure at Min. Yield (psi) LTC	Internal Yield Pressure at Min. Yield (psi) BTC	Joint Strength 1000 lbs STC	Joint Strength 1000 lbs BTC	Body Yield 1000 lbs	Wall (in.)	I.D. (in.)
4.500	11.60	11.36	J55	4960	5350	5350	5350	5350	154	225	184	0.250	4.000
4.500	11.60	11.36	K55	4960	5350	5350	5350	5350	170	277	184	0.250	4.000
4.500	11.60	11.36	L80	6350	7780	7780	7780	7780	291	267	0.250	4.000	
4.500	11.60	11.36	N80	6350	7780	7780	7780	7780	304	267	0.250	4.000	
4.500	11.60	11.36	C95	7030	9240	9240	9240	9240	325	317	0.250	4.000	
4.500	11.60	11.36	P110	7580	10690	10690	10690	10690	385	367	0.250	4.000	
4.500	11.60	11.36	P110HC	8650	10690	10690	10690	10690	385	367	0.250	4.000	
4.500	13.50	13.05	L80	8540	9020	9020	9020	9020	334	307	0.290	3.920	
4.500	13.50	13.05	N80	8540	9020	9020	9020	9020	349	307	0.290	3.920	
4.500	13.50	13.05	C95	9660	10710	10710	10710	10710	374	364	0.290	3.920	
4.500	13.50	13.05	P110	10680	12410	12410	12410	12410	443	422	0.290	3.920	
4.500	15.10	15.00	P110	14350	14420	14420	13460	13460	509	485	0.337	3.826	
5.000	15.00	14.88	J55	5560	5700	5700	5700	5700	207	293	241	0.296	4.408
5.000	15.00	14.88	K55	5560	5700	5700	5700	5700	228	359	241	0.296	4.408
5.000	15.00	14.88	L80	7250	8290	8290	8290	8290	379	350	0.296	4.408	
5.000	15.00	14.88	N80	7250	8290	8290	8290	8290	396	350	0.296	4.408	
5.000	15.00	14.88	C95	8110	9840	9840	9840	9840	424	416	0.296	4.408	
5.000	15.00	14.88	P110	8850	11400	11400	11400	11400	503	481	0.296	4.408	
5.000	18.00	17.95	L80	10500	10140	10140	9910	9910	457	422	0.362	4.151	
5.000	18.00	17.95	N80	10500	10140	10140	9910	9910	477	422	0.362	4.151	
5.000	18.00	17.95	C95	12030	12040	12040	11770	11770	512	501	0.362	4.151	
5.000	18.00	17.95	P110	13470	13940	13940	13620	13620	606	580	0.362	4.151	
5.000	23.20	23.11	L80	13830	13380	10820	9910	9910	510	543	0.478	4.044	
5.000	23.20	23.11	N80	13830	13380	10820	9910	9910	537	543	0.478	4.044	
5.000	23.20	23.11	C95	16430	15890	12850	11770	11770	563	645	0.478	4.044	
5.000	23.20	23.11	P110	19020	18400	14880	13630	13630	671	747	0.478	4.044	